



Mirror Shield

Protection from Acid Etching

Background

A new method employed by graffiti vandals or “taggers” is the use of glass etching compounds on mirror surfaces. These over the counter items usually contain hydrofluoric, ammonium bifluoride and/or sulfuric acids. These etching compounds can be mixed with shoe polish and applied to mirrors where they will react with the mirror surface within minutes. The use of polyester film as a sacrificial barrier has been found to be very useful in preventing damage to mirrors by physical and chemical attack.



Test Matrix

Mirror Shield was tested for its protective capabilities against readily available glass etching materials. Armour Etch® glass etching cream and Etch Bath® glass dipping solution were applied to Mirror Shield on ordinary common stock mirror. The test panels were placed in a horizontal position (worse case) and the etch compounds were left in contact with the film for 24, 48 and 72 hours. The results from the exposures are listed below.

Film	24 Hours	48 Hours	72 Hours
Bare Mirror	Severe (5 minutes)	N/A	N/A
Mirror Shield Etch Cream	No damage	No damage	No damage
Mirror Shield Etch Solution	No damage	No damage	No damage

Conclusion

Neither the Etch Cream, nor the Etch Bath, caused mirror damage during the extended test duration with Mirror Shield.

The experiment was carried out in a horizontal orientation. More commonly, mirrors are vertical thus allowing for run-off. Furthermore, the effect of exterior environmental factors, solar heat, wind, etc. would cause these etchants to dissipate faster; decreasing the actual duration the etchant is in contact with the mirror. Worth noting, the Etch Bath material is extremely low in viscosity and does not wet out the film’s surface well. The liquid etch would run off vertically installed glass rather quickly.

Armour Etch® and Etch Bath® are registered trademarks of Armour Products.