



Mirror Shield

Physical Characteristics

PERFORMANCE	VALUE	METHOD
Thickness		
Mirror Shield only (no liner)	125 micron (5 mil)	
Mirror Shield with liner	200 micron (8 mil)	
Physical		
Tensile Strength	28,000 – 30,000 lbs/psi	ASTM D 882
Break Strength	190 lbs/inch width	ASTM D 882
Elongation at Break	>100%	ASTM D 882
Peel Strength	1,000 g/inch	ASTM D 3330
Puncture Strength	141 lbs	ASTM D 4830
Abrasion Resistance (a)	<3%	ASTM D 523 & ANSI Z26.1 Test 17
Chemical Resistance	Pass	ANSI Z26.1 Test 19
Acid Resistance	72 hrs. No damage	

(a) Abrasion Resistance: Film must have a surface coating that is resistant to abrasion such that, a gloss factor less than 3% at 20 degrees, 60 degrees, and 85 degrees per ANSI Z26.1 Test 17 and ASTM D 523.

Storage

Store in a dry, controlled environment. The temperature should not exceed 95° F (35° C) nor go below 50° F (10° C). The film should always be stored in the original packaging with the end plugs securely placed on the core.

Disclaimer

These test data contain only results arrived at after employing specific test procedures and standards. The included data do not constitute a recommendation for, endorsement of, or certification of the product or material tested. These data are provided for informational purposes only and are not to be considered part of the basic representation or warranty, expressed or implied, including the implied warranties of merchantability or fitness for a particular purpose, that its products will conform to these test data. Solar Gard's limited warranty should be carefully reviewed prior to purchasing any Solar Gard product. Extrapolation of data from the sample or samples relation to the batch or lot from which data were obtained may not correlate and should be interpreted accordingly with caution. Solar Gard shall not be responsible for variations in quality, composition, appearance, performance or other feature of similar subject matter produced by persons or under conditions over which Solar Gard has no control.

www.solargard.com

Saint-Gobain Performance Plastics
 4540 Viewridge Avenue
 San Diego, CA 92123
 Tel: 877.273.4364
 E-mail: info@solargard.com

PDF0345MIRSINT 10/17
 © Copyright 2017, Saint-Gobain Performance Plastics and/or its affiliates
 All Rights Reserved • www.solargard.com

Please recycle