

## **IMPACT TESTING ON SAFETY GLAZING MATERIAL**

Rendered to:

## SAINT-GOBAIN PERFORMANCE PLASTICS - SOLAR GARD LLC 8575 A Somerset Drive Largo, Florida 33773

Report No:	C2390.01-122-42
Test Date:	09/11/12
Report Date:	09/17/12
Revision 1:	09/18/12

Sample ID: Solar Gard® Armorcoat® 11 mil (Set 1) 6 mm Film-backed Transparent Glass

Samples Provided By: Saint-Gobain Performance Plastics–Solar Gard – San Diego, California Lab Temperature: 21°C

Duration of Pre-Conditioning @ 21° - 23°C: 24 Hours

Test Size: 876 mm wide by 1938 mm high

All test specimens were destroyed by test or by our personnel and have been disposed of as trash. Note: Impacted from film side only with film clamped in frame.

Impact Level	Drop Height	Spec. No.	Test Standard	Thickness (mm)	Observations	Fragment Weight (grams)	Performance Classification
3 190 mm		1	EN 12600	5.92	No openings		
	190	2		5.94	Did not break		
	3	EN 12600	5.92	No openings			
		4		5.91	No openings		
2 450 mm		1	2 3 EN 12600	5.92	No openings	41	
	450	2		5.94	No openings	14	
	mm	3		5.89	No openings	26	
		4		5.91	No openings	76	
1	1200 mm	1		5.85	No openings	9	1 (B) 1
		2	EN 12600	5.96	No openings	6	1 (B) 1
		3		5.85	No openings	21	1 (B) 1
		4		5.92	No openings	11	1 (B) 1

**Impact Tests**: (EN 12600:2002)

\*Acceptance Criteria = 24.95 x lite thickness in mm.

130 Derry Court York, PA 17406-8405 phone: 717-764-7700 fax: 717-764-4129 www.archtest.com



## Film Thickness:

Measured Sample	Overall Thickness (mm)	Glass Only Thickness (mm)	Film Thickness (mm)	Film Designation
Level 3 Specimen #1	5.92	5.60	0.42	11 mil Armorcoat®

Conclusion: Meets EN 12600 classification 1(B)1.



C2390.01-122-42 Page 3 of 3 Revision 1: 09/18/12

Detailed drawings, data sheets, representative samples of test specimens (if sampled), a copy of this report, or other pertinent project documentation will be retained by Architectural Testing, Inc. for a period of four years from the original report date. At the end of this retention period, such materials shall be discarded without notice and the service life of this report will expire. Results obtained are tested values and were secured by using the designated test methods. This report does not constitute certification of this product nor an opinion or endorsement by this laboratory. It is the exclusive property of the client so named herein and relates only to the specimen(s) tested. This report may not be reproduced, except in full, without the written approval of Architectural Testing, Inc.

For ARCHITECTURAL TESTING, INC.:

Todd M. Wilt Technician I TMW:cmd Scott T. Swaltek, P.E. Senior Project Engineer

## **Revision Log**

<u>Rev. #</u>	Date	Page(s)	Revision(s)
0	09/17/12	N/A	Original report issue
1	09/18/12	1	Corrected location of manufacturer to San Diego, California

